



Manufactured In The USA

## Certificate of Conformance

This is to certify that the product stated below is of the same classification, manufacturing process, and material requirements as the electrode used for the testing on the date stated. All tests required by the specifications for classification were performed and the material met all requirements. It was manufactured and supplied according to the quality management system of Select-Arc, Inc., which meets the requirements of ISO 9001 and other applicable specifications. This certificate complies with the requirements of EN 10204, Type 2.2.

Product: SelectAlloy 309L-AP  
Diameter(s): .045 - 1/16  
Specifications: AWS A5.22:2012  
Classification: E309LT1-1, E309LT1-4

Test Completion Date: 1/24/2018  
Lot Numbers: (.045) 0622  
(1/16) 0622

### Chemical Analysis (wt%)

Diameter		.045		1/16		
Shielding Gas		75-80% Ar / Bal CO2	CO2	75-80% Ar / Bal CO2	CO2	
	Max	Min	Results	Results	Results	Results
<b>C</b>	0.04	-	0.04	0.04	0.03	0.03
<b>Cr</b>	25.0	22.00	24.4	23.5	24.8	24.3
<b>Cu</b>	0.50	-	0.13	0.14	0.13	0.13
<b>Mn</b>	2.50	0.50	0.96	0.96	1.11	0.95
<b>Mo</b>	0.50	-	0.18	0.17	0.17	0.18
<b>Ni</b>	14.0	12.00	12.7	12.9	12.6	13.0
<b>P</b>	0.040	-	0.021	0.024	0.019	0.020
<b>S</b>	0.030	-	0.004	0.007	0.003	0.003
<b>Si</b>	1.00	-	0.63	0.60	0.76	0.59

*This product contains Bismuth at levels >.002 wt%*

Radiographic Test: Met Requirement  
Fillet Weld Test: Met Requirement  
Bend Test: Met Requirement


### Weld Parameters

Electrode Diameter:	1/16	
Shielding Gas	75-80% Ar / Bal CO2	CO2
Amperage:	215	215
Arc Voltage:	26.0	29.0
Current Polarity:	DCEP	DCEP
Electrical Extension(in):	5/8	5/8
No. of Passes/Layers:	13/6	12/6
Interpass Temperature(°F):	300	300

### Mechanical Properties

Electrode Diameter:		1/16	
Shielding Gas		75-80% Ar / Bal CO2	CO2
Requirements		Results	Results
Test Condition:	As-Welded	As-Welded	As-Welded
PWHT Temperature:	-	-	-
Tensile Strength (psi):	75000 min	88000	82000
Yield Strength (psi):	-	64000	61000
Elongation (%):	30 min	37	38

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification.

Signed By:   
\_\_\_\_\_  
**Martin L. Caruso, Director of Technology**