

Certificate of Conformance

This is to certify that the product stated below is of the same classification, manufacturing process, and material requirements as the electrode used for the testing on the date stated. All tests required by the specifications for classification were performed and the material met all requirements. It was manufactured and supplied according to the quality management system of Select-Arc, Inc., which meets the requirements of ISO 9001 and other applicable specifications. This certificate complies with the requirements of EN 10204, Type 2.2.

Product: SelectAlloy 309L
 Diameter(s): .045 - 1/16
 Specifications: AWS A5.22:2012
 Classification: E309LT0-1, E309LT0-4

Test Completion Date: 11/30/2017
 Lot Numbers: (.045) 0611
 (1/16) 0611

Chemical Analysis (wt%)

Diameter		.045		1/16	
Shielding Gas		75-80% Ar / Bal CO2	CO2	75-80% Ar / Bal CO2	CO2
	Max	Min	Results	Results	Results
C	0.04	-	0.03	0.03	0.04
Cr	25.00	22.00	23.29	23.34	23.61
Cu	0.75	-	0.16	0.16	0.16
Mn	2.50	0.50	1.70	1.60	1.60
Mo	0.75	-	0.10	0.10	0.10
Ni	14.00	12.00	13.15	12.90	12.78
P	0.040	-	0.021	0.019	0.020
S	0.030	-	0.007	0.006	0.004
Si	1.00	-	0.93	0.96	0.91

Weld Parameters

Electrode Diameter:	1/16	
Shielding Gas	75-80% Ar / Bal CO2	CO2
Amperage:	207	226
Arc Voltage:	27.5	28.5
Current Polarity:	DCEP	DCEP
Electrical Extension(in):	3/4	3/4
No. of Passes/Layers:	13/6	13/6
Interpass Temperature(°F):	300	300

Mechanical Properties


Electrode Diameter:		1/16	
Shielding Gas		75-80% Ar / Bal CO2	CO2
Requirements		Results	Results
Test Condition:	As-Welded	As-Welded	As-Welded
PWHT Temperature:	-	-	-
Tensile Strength (psi):	80000 min	85000	83000
Yield Strength (psi):	-	63000	62000
Elongation (%):	30 min	35	35

This product contains Bismuth at levels >.002 wt%

Radiographic Test: Met Requirement
 Bend Test: Met Requirement

The undersigned certifies that the product supplied will meet the requirements of the applicable AWS Filler Metal Specification when tested in accordance with that specification.

Signed By: _____



Martin L. Caruso, Director of Technology