

## Select 910-B3L

### Description:

**Select 910-B3L** is a low alloy steel electrode for flux cored arc welding with external gas shielding. This electrode is intended for single and multiple pass welding, in all positions, of certain 2¼% Cr - 1% Mo steel plate and pipe, where lower carbon levels are required in the weld deposit. Carbon dioxide is the recommended shielding gas; mixtures of 75-80% argon-balance carbon dioxide may be employed, however, the use of this gas may increase tensile strength beyond AWS requirements. Gas flow rate should be maintained at 35-50 cfh, and the dew point must be -40°F or lower.

### Classifications:

- E91T1-B3LC, E91T1-B3LM per AWS A5.29, SFA 5.29

### Characteristics:

**Select 910-B3L** is a premium low alloy steel, flux cored electrode, with superb welder appeal and excellent mechanical properties. The smooth arc transfer, low spatter, and fast freezing slag make this an excellent choice for welding boiler and pressure vessel components in all positions. **Select 910-B3L** produces a low carbon, 2¼% Cr- 1% Mo deposit that has improved ductility and lower hardness when compared to conventional, higher carbon grades. **Select-Arc** employs the latest manufacturing technology, ensuring the ultimate in quality, consistency, and weld performance, to maximize the capabilities of **Select 910-B3L** and the weld metal it deposits.

### Applications:

**Select 910-B3L** is intended to weld thin walled A335-P22 pipe for use in the as-welded condition or for applications where low hardness is necessary. These materials are used in the fabrication of boilers, heat exchangers, and pressure vessels. The AWS classification requires no minimum toughness values for this electrode; therefore, any specific toughness requirements should be discussed prior to use of the electrode.

### Typical Mechanical Properties (CO<sub>2</sub>):

	SR 1 Hr. at 1275° F
Ultimate Tensile Strength (psi)	94,200
Yield Strength (psi)	81,400
Percent Elongation	22

### Typical Deposit Composition:

Wt%	C	Mn	Si	P	S	Cr	Mo
	.03	.70	.30	.010	.010	2.20	1.03

### Recommended Welding Parameters:

Diameter	Position	Optimum			Range	
		Amperage	WFS	Voltage	Amperage	Voltage
1/16"	Flat	350	350	29	150-400	22-34
	Overhead	225	170	26	150-310	22-28
	Vertical up	225	170	25	150-280	22-27
.052"	Flat	300	440	28	100-330	19-32
	Overhead	200	245	26	150-310	21-28
	Vertical up	200	245	25	150-280	21-27
.045"	Flat	250	450	28	100-300	21-32
	Overhead	200	300	26	150-280	21-29
	Vertical up	200	300	25	100-230	21-28

Rev 0 (03/07/2014)

Notice: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. Select-Arc disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.