

# Select 105-D2

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Low alloy steel electrode designed to weld certain manganese-molybdenum steels (such as ASTM A302) and castings (such as ASTM A49, A291, and A735)
- Basic slag system allows the product to exhibit excellent low temperature impact properties

## CONFORMANCES

AWS A5.29

E100T5-D2C

## DIAMETERS (in [mm])

3/32 (2.4)

## POSITIONS



## SHIELDING GAS

100% CO<sub>2</sub>

Flow Rate: 40 - 50 CFM

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Mn	Mo	P	S	Si
100%CO <sub>2</sub>	0.08	2.01	0.49	0.013	0.010	0.25

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -40°F (-40°C) ft-lb (J)
100%CO <sub>2</sub>	110 (759)	96 (664)	24	PWHT	1150°F for 1 hr	41 (56)

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
3/32 (2.4 mm)	100% CO <sub>2</sub>	Flat & Horizontal	145 (3.7)	320	25	1 (25)
		Flat & Horizontal	160 (4.1)	345	27	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	170 (4.3)	370	29	1 1/4 - 1 1/2 (32 - 38)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

## PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## **STORAGE AND HANDLING**

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 9/13/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

**600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • [www.Select-SAI.com](http://www.Select-SAI.com)**