

Select 110-K3

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Intended for single and multiple pass welding of structural steel and fabrications utilizing high strength, low alloy steels, such as HY-100 and ASTM A514 type alloys.
- The arc transfer mode is a smooth, small to medium ball transfer that produces minimal spatter.
- Slag removes easily with no residual slag where minimal clean-up is required.
- Typical applications include low temperature storage tanks, offshore drilling rigs, shipbuilding, and construction machinery where excellent low-temperature toughness is required.

CONFORMANCES

| | |
|---------------|---------------|
| AWS A5.29 | E110T1-K3C-H8 |
| ASME SFA 5.29 | E110T1-K3C-H8 |

DIAMETERS (in [mm])

0.045 (1.2), 0.052 (1.3), 1/16 (1.6), 5/64 (2.0), 3/32 (2.4)

POSITIONS



SHIELDING GAS

100% CO₂

Flow Rate: 40 - 50 CFH

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

| Shielding Gas | C | Cr | Mn | Mo | Ni | P | S | Si | V |
|---------------------|------|------|------|------|------|-------|-------|------|------|
| 100%CO ₂ | 0.07 | 0.04 | 1.54 | 0.49 | 2.29 | 0.009 | 0.010 | 0.34 | 0.02 |

TYPICAL MECHANICAL PROPERTIES

| Shielding Gas | Tensile Strength ksi (MPa) | Yield Strength ksi (MPa) | Elongation (%) | Weld Condition | PWHT Temp | CVN @ 0°F (-20°C) ft-lb (J) |
|---------------------|-------------------------------|-----------------------------|-------------------|-------------------|--------------|-----------------------------------|
| 100%CO ₂ | 116 (800) | 105 (724) | 19 | As-Welded | - | 38 (52) |



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS **

| Diameter in (mm) | Shielding Gas | Position | WFS* in/min (m/min) | Amps | Volts | CTWD* in (mm) |
|------------------|---------------|-------------------|---------------------|------|-------|-------------------------|
| 0.045 (1.2 mm) | 100% CO2 | Flat & Horizontal | 250 (6.4) | 175 | 24 | 5/8 (16) |
| | | Flat & Horizontal | 340 (8.6) | 205 | 27 | 5/8 - 3/4 (16 - 19) |
| | | Flat & Horizontal | 440 (11.2) | 235 | 29 | 5/8 - 3/4 (16 - 19) |
| 0.052 (1.3 mm) | 100% CO2 | Flat & Horizontal | 245 (6.2) | 210 | 24 | 3/4 - 1 (19 - 25) |
| | | Flat & Horizontal | 250 (6.4) | 310 | 27 | 3/4 - 1 (19 - 25) |
| | | Flat & Horizontal | 280 (7.1) | 395 | 29 | 3/4 - 1 (19 - 25) |
| 1/16 (1.6 mm) | 100% CO2 | Flat & Horizontal | 235 (6.0) | 245 | 24 | 3/4 (19) |
| | | Flat & Horizontal | 280 (7.1) | 275 | 27 | 3/4 - 1 (19 - 25) |
| | | Flat & Horizontal | 325 (8.3) | 320 | 29 | 3/4 - 1 (19 - 25) |
| 5/64 (2.0 mm) | 100% CO2 | Flat & Horizontal | 145 (3.7) | 280 | 25 | 1 (25) |
| | | Flat & Horizontal | 190 (4.8) | 320 | 27 | 1 - 1 1/4 (25 - 32) |
| | | Flat & Horizontal | 230 (5.8) | 365 | 29 | 1 - 1 1/4 (25 - 32) |
| 3/32 (2.4 mm) | 100% CO2 | Flat & Horizontal | 120 (3.0) | 275 | 25 | 1 1/4 (32) |
| | | Flat & Horizontal | 150 (3.8) | 335 | 27 | 1 1/4 - 1 1/2 (32 - 38) |
| | | Flat & Horizontal | 165 (4.2) | 400 | 29 | 1 1/4 - 1 1/2 (32 - 38) |

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

**The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.