Low Alloy / Gas Shielded / Flux Cored

**PRODUCT DATA SHEET** 

# **FEATURES**

- This electrode is capable of single and multiple pass welding and is designed for 100%CO2 shielding gas.
- Meets the same requirements as E11018-M covered electrodes.
- The arc transfer is globular with a convex bead profile due to the nature of a basic slag system.
- Excellent low temperature CVN toughness and low diffusible hydrogen levels.
- Ideal selection for welding high strength, low alloy steels such as T-1, ASTM A514 and HY-100; and for welding abrasion resistant steels in the 300, 350 and 400 series.

#### **CONFORMANCES**

AWS A5.29

E110T5-K3C-H4

# **DIAMETERS (in (mm))**

0.045 (1.2), 1/16 (1.6), 3/32 (2.4)

## **POSITIONS**



## **SHIELDING GAS**

100% CO2

Flow Rate: 40 - 50 CFM

## **POLARITY**

Direct Current Electrode Positive (DCEP)

## **TYPICAL WELD DEPOSIT CHEMISTRY (WT%)**

Shielding Gas	С	Cr	Mn	Мо	Ni	P	S	Si	V
100%CO2	0.04	0.06	1.64	0.46	2.01	0.010	0.010	0.46	0.009

# **TYPICAL MECHANICAL PROPERTIES**

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -60°F (-50°C) ft-lb (J)
100%CO2	116 (800)	104 (717)	20	As-Welded	-	39 (53)



Revision: 9/14/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

#### RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
	100% CO2	Flat & Horizontal	275 (7.0)	160	25	1/2 - 5/8 (13 - 16)
0.045 (1.2 mm)		Flat & Horizontal	350 (8.9)	190	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	435 (11.0)	220	29	5/8 - 3/4 (16 - 19)
	100% CO2	Flat & Horizontal	250 (6.4)	265	25	3/4 (19)
1/16 (1.6 mm)		Flat & Horizontal	280 (7.1)	290	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	315 (8.0)	315	29	3/4 - 1 (19 - 25)
	100% CO2	Flat & Horizontal	145 (3.7)	320	25	1 (25)
3/32 (2.4 mm)		Flat & Horizontal	160 (4.1)	345	27	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	170 (4.3)	370	29	1 1/4 - 1 1/2 (32 - 38)

<sup>\*</sup> WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

# PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

## **STORAGE AND HANDLING**

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 9/14/2022

<sup>\*</sup>Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.