

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- The basic slag system provides better mechanical properties and lower diffusible hydrogen levels in the weld deposit than T-1 (rutile) slag systems.
- Arc transfer is globular and more spatter is produced than with T-1 slag systems.
- Select 115-K4 is an improved T-5 electrode with slag removal and bead geometry similar to that of E10018 electrodes
- Ideal for welding T-1, HY-100, ASTM A514, and other HSLA steels of similar strength.

CONFORMANCES

AWS A5.29

E110T5-K4C

DIAMETERS (in (mm))

0.045 (1.2), 1/16 (1.6), 3/32 (2.4)

POSITIONS



SHIELDING GAS

100% CO2

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	С	Cr	Mn	Мо	Ni	P	S	Si	V
100%CO2	0.06	0.50	1.79	0.46	2.30	0.007	0.011	0.52	0.01

TYPICAL MECHANICAL PROPERTIES

	Shielding Gas	Tensile Strength ksi (MPa)	ength Strength Elong		Weld Condition	PWHT Temp	CVN @ -60°F (-50°C) ft-lb (J)
Ī	100%CO2	128 (880)	113 (779)	21	As-Welded	-	34 (46)



Revision: 9/26/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
	100% CO2	Flat & Horizontal	275 (7.0)	160	25	1/2 - 5/8 (13 - 16)
0.045 (1.2 mm)		Flat & Horizontal	350 (8.9)	190	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	435 (11.0)	220	29	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	250 (6.4)	265	25	3/4 (19)
1/16 (1.6 mm)	100% CO2	Flat & Horizontal	280 (7.1)	290	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	315 (8.0)	315	29	3/4 - 1 (19 - 25)
	100% CO2	Flat & Horizontal	145 (3.7)	320	25	1 (25)
3/32 (2.4 mm)		Flat & Horizontal	160 (4.1)	345	27	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	170 (4.3)	370	29	1 1/4 - 1 1/2 (32 - 38)

^{*} WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 9/26/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

^{*}Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.