

# Select 121-K3M

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Microalloying and slag adjustments provide enhanced CVN toughness values at temperatures of at least -40° F (or °C).
- Well suited for offshore drilling rigs, low temperature storage tanks, ship building, and high strength and toughness applications.
- Smooth arc transfer and excellent bead geometry considering the higher alloyed nature of this product.

## CONFORMANCES


AWS A5.29

E121T1-GM-H4

## DIAMETERS (in [mm])

0.045 (1.2), 0.052 (1.3)

## POSITIONS



## SHIELDING GAS

75-80% Ar / Balance CO<sub>2</sub>

Flow Rate: 40 - 50 CFH

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

Shielding Gas	C	Cr	Mn	Mo	Ni	P	S	Si	V
75%Ar / 25%CO <sub>2</sub>	0.06	0.06	2.00	0.38	2.50	0.012	0.009	0.37	0.01

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -40°F (-40°C) ft-lb (J)	CVN @ -60°F (-50°C) ft-lb (J)
75%Ar / 25%CO <sub>2</sub>	130 (897)	119 (821)	18	As-Welded	-	37 (50)	26 (35)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## RECOMMENDED WELDING PARAMETERS \*\*

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO2	All Positions	200 (5.1)	145	23	1/2 - 5/8 (13 - 16)
		All Positions	235 (6.0)	160	24	1/2 - 5/8 (13 - 16)
		All Positions	300 (7.6)	185	26	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	215	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	29	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	75% Ar/25% CO2	All Positions	170 (4.3)	155	23	5/8 - 3/4 (16 - 19)
		All Positions	200 (5.1)	175	24	5/8 - 3/4 (16 - 19)
		All Positions	250 (6.4)	225	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	310 (7.9)	250	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	395 (10.0)	280	29	3/4 - 1 (19 - 25)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

\*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

## APPROVALS

Agency	Approval	Shielding Gas	Diameter(s) in (mm)
ABS	E121T1-GM-H4	M21 (75%Ar / 25%CO2)	0.045 (1.2) - 0.052 (1.3)

## PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.