

# Select 125-K4M

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Designed for welding of low alloy steels, such as ASTM A514 or HY-100. Also well suited for structural welding and general fabrication.
- Basic slag system allows for excellent mechanical properties.
- In contrast with T-1 slag systems, this electrode has a globular transfer. However, the welding performance is improved over usual T-5 slag systems, featuring excellent slag release and bead geometry.
- Typical applications include mining machinery, cranes, and construction equipment.
- Designed for 75-80% Ar / balance CO<sub>2</sub> shielding gas. If you wish to use 100% CO<sub>2</sub>, Select 125-K4C is the preferred choice

## CONFORMANCES

AWS A5.29

E120T5-K4M-H4

## DIAMETERS (in [mm])

1/16 (1.6), 3/32 (2.4)

## POSITIONS



## SHIELDING GAS

75-80% Ar/Balance CO<sub>2</sub>

Flow Rate: 40 - 50 CFH

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Mn	Mo	Ni	P	S	Si	V
75%Ar / 25%CO <sub>2</sub>	0.08	0.43	1.98	0.39	2.51	0.006	0.010	0.62	0.004

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -60°F (-50°C) ft-lb (J)
75%Ar / 25%CO <sub>2</sub>	134 (924)	112 (772)	19	As-Welded	-	39 (53)



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • [www.Select-Arc.com](http://www.Select-Arc.com)

## RECOMMENDED WELDING PARAMETERS \*\*

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
1/16 (1.6 mm)	75% Ar/25% CO2	Flat & Horizontal	250 (6.4)	265	24	3/4 (19)
		Flat & Horizontal	280 (7.1)	290	26	3/4 - 1 (19 - 25)
		Flat & Horizontal	315 (8.0)	315	28	3/4 - 1 (19 - 25)
3/32 (2.4 mm)	75% Ar/25% CO2	Flat & Horizontal	120 (3.0)	275	24	1 1/4 (32)
		Flat & Horizontal	150 (3.8)	335	26	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	165 (4.2)	400	28	1 1/4 - 1 1/2 (32 - 38)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

\*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

## PACKAGING [lbs (kgs)]

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • [www.Select-Arc.com](http://www.Select-Arc.com)