

# Select 410NiMo-C Mod

Stainless Steel / Gas Shielded / Metal Cored

PRODUCT DATA SHEET

## FEATURES

- Modified chemistry from EC410NiMo alloy to improve CVN toughness results.
- Metal cored construction inherently provides better welding performance compared to solid wires
- Used to weld CA6NM castings or similar materials, as well as light-gauge 405, 410, and 410S base metals.

## CONFORMANCES

AWS A5.22

ECG

ASME SFA 5.22

ECG

## DIAMETERS (in [mm])

0.045 (1.2), 1/16 (1.6)

## POSITIONS



## SHIELDING GAS

Ar + 0.5-5% CO<sub>2</sub>, Ar + 0.5-3% O<sub>2</sub>

Flow Rate: 40 - 50 CFH

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si
Argon	0.02	12.40	0.04	1.05	0.50	4.75	0.010	0.011	0.70

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ 32°F (0°C) ft-lb (J)
98%Ar / 2%O <sub>2</sub>	120 (828)	93 (641)	21	PWHT	600°C for 8 hrs	48 (65)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## RECOMMENDED WELDING PARAMETERS \*\*

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	98% Ar/2% O <sub>2</sub>	Flat & Horizontal	280 (7.1)	200	20	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	350 (8.9)	220	21	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	400 (10.2)	250	23	5/8 (16)
		Flat & Horizontal	475 (12.1)	275	25	5/8 (16)
1/16 (1.6 mm)	98% Ar/2% O <sub>2</sub>	Flat & Horizontal	225 (5.7)	260	21	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	265 (6.7)	285	22	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	300 (7.6)	310	23	3/4 - 1 (19 - 25)
		Flat & Horizontal	350 (8.9)	335	25	3/4 - 1 (19 - 25)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

\*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

## PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.