

# Select 7000-SRC

Carbon Steel / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Specifically developed to maintain tensile strength and high toughness at low temperatures after long term or repeated post-weld heat treatment.
- Ideal for pressure vessels, flanges and valves, piping and repair applications.
- Maintains low hardness in the as-welded and heat treated conditions

## CONFORMANCES

AWS A5.20

E71T-12C-JH4


E71T-1C-H4

E71T-9C-JH4

## DIAMETERS (in [mm])

0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

## POSITIONS



## SHIELDING GAS

100% CO<sub>2</sub>

Flow Rate: 40 - 50 CFH

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

| Shielding Gas       | C    | Cr   | Cu   | Mn   | Mo    | Ni   | P     | S     | Si   | V     |
|---------------------|------|------|------|------|-------|------|-------|-------|------|-------|
| 100%CO <sub>2</sub> | 0.05 | 0.07 | 0.03 | 1.35 | 0.005 | 0.38 | 0.012 | 0.008 | 0.30 | 0.005 |

## TYPICAL MECHANICAL PROPERTIES

| Shielding Gas       | Tensile Strength<br>ksi (MPa) | Yield Strength<br>ksi (MPa) | Elongation<br>(%) | Weld<br>Condition | PWHT<br>Temp      | CVN @<br>-40°F (-40°C)<br>ft-lb (J) | CVN @<br>-60°F (-50°C)<br>ft-lb (J) |
|---------------------|-------------------------------|-----------------------------|-------------------|-------------------|-------------------|-------------------------------------|-------------------------------------|
| 100%CO <sub>2</sub> | 80 (548)                      | 68 (466)                    | 32                | As-Welded         | -                 | 101 (137)                           | 88 (119)                            |
| 100%CO <sub>2</sub> | 78 (541)                      | 64 (439)                    | 30                | PWHT              | 1150°F for 16 hrs | 59 (80)                             | 45 (61)                             |
| 100%CO <sub>2</sub> | 75 (519)                      | 61 (421)                    | 34                | PWHT              | 1150°F for 8 hrs  | 105 (142)                           | 89 (121)                            |



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## RECOMMENDED WELDING PARAMETERS \*\*

| Diameter in (mm) | Shielding Gas | Position          | WFS* in/min (m/min) | Amps | Volts | CTWD* in (mm)       |
|------------------|---------------|-------------------|---------------------|------|-------|---------------------|
| 0.045 (1.2 mm)   | 100% CO2      | All Positions     | 200 (5.1)           | 145  | 23    | 1/2 - 5/8 (13 - 16) |
|                  |               | All Positions     | 235 (6.0)           | 160  | 24    | 1/2 - 5/8 (13 - 16) |
|                  |               | All Positions     | 300 (7.6)           | 185  | 26    | 1/2 - 5/8 (13 - 16) |
|                  |               | Flat & Horizontal | 375 (9.5)           | 215  | 27    | 5/8 - 3/4 (16 - 19) |
|                  |               | Flat & Horizontal | 440 (11.2)          | 235  | 29    | 5/8 - 3/4 (16 - 19) |
| 0.052 (1.3 mm)   | 100% CO2      | All Positions     | 170 (4.3)           | 155  | 23    | 5/8 - 3/4 (16 - 19) |
|                  |               | All Positions     | 200 (5.1)           | 175  | 24    | 5/8 - 3/4 (16 - 19) |
|                  |               | All Positions     | 250 (6.4)           | 225  | 26    | 5/8 - 3/4 (16 - 19) |
|                  |               | Flat & Horizontal | 310 (7.9)           | 250  | 27    | 3/4 - 1 (19 - 25)   |
|                  |               | Flat & Horizontal | 395 (10.0)          | 280  | 29    | 3/4 - 1 (19 - 25)   |
| 1/16 (1.6 mm)    | 100% CO2      | All Positions     | 125 (3.2)           | 165  | 23    | 5/8 - 3/4 (16 - 19) |
|                  |               | All Positions     | 150 (3.8)           | 195  | 24    | 5/8 - 3/4 (16 - 19) |
|                  |               | All Positions     | 185 (4.7)           | 225  | 26    | 5/8 - 3/4 (16 - 19) |
|                  |               | Flat & Horizontal | 265 (6.7)           | 280  | 27    | 3/4 - 1 (19 - 25)   |
|                  |               | Flat & Horizontal | 325 (8.3)           | 320  | 29    | 3/4 - 1 (19 - 25)   |

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

\*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

## PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.