

# Select 700GS

Carbon Steel / Self Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- SELECT 700GS is a carbon steel, flux cored electrode for use without an external shielding gas and should be welded with DCEN (straight polarity).
- The arc transfer is smooth and stable, with virtually no spatter emission. This "soft" arc transfer minimizes burn-through on thin gauge material.
- This slag system enables the electrode to weld in all positions and to make welds at high speed.
- Intended for welding thin-gauge carbon steel, ranging from 3/16 " to 22 gauge, applications are limited to single-pass weldments.
- This product is designed to weld quite effectively over galvanized material and can be used on certain aluminized surfaces as well.
- Select 700GS is an ideal choice for applications such as lap and butt welds on galvanized sheet metal, repair of automobile sheet metal, welding ductwork, and joining of galvanized roofing sheet metal.

## CONFORMANCES

AWS A5.20


E71T1-14

E71T1-GS

## DIAMETERS (in [mm])

0.030 (0.8), 0.035 (0.9), 0.045 (1.2), 1/16 (1.6), 0.068 (1.7)

## POSITIONS



## SHIELDING GAS

N/A

## POLARITY

Direct Current Electrode Negative (DCEN)

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Weld Condition	PWHT Temp
N/A	86 (596)	As-Welded	-



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.030 (0.8 mm)	N/A	Flat & Horizontal	225 (5.7)	100	16	1/2 (13)
		Flat & Horizontal	375 (9.5)	150	17	1/2 (13)
		Flat & Horizontal	445 (11.3)	175	17	1/2 (13)
		All Positions	80 (2.0)	50	15	3/8 (10)
0.035 (0.9 mm)	N/A	Flat & Horizontal	110 (2.8)	100	16	3/8 (10)
		Flat & Horizontal	180 (4.6)	150	17	1/2 (13)
		Flat & Horizontal	305 (7.7)	200	18	1/2 (13)
		All Positions	70 (1.8)	75	15	3/8 (10)
0.045 (1.2 mm)	N/A	All Positions	70 (1.8)	100	15	1/2 (13)
		Flat & Horizontal	120 (3.0)	150	16	1/2 (13)
		Flat & Horizontal	195 (5.0)	200	17	5/8 (16)
		Flat & Horizontal	245 (6.2)	225	18	5/8 (16)
1/16 (1.6 mm)	N/A	All Positions	60 (1.5)	150	17	1/2 (13)
		Flat & Horizontal	85 (2.2)	200	18	1/2 (13)
		Flat & Horizontal	135 (3.4)	250	18	5/8 (16)
		Flat & Horizontal	180 (4.6)	300	19	3/4 (19)
0.068 (1.7 mm)	N/A	All Positions	55 (1.4)	180	17	1/2 (13)
		Flat & Horizontal	80 (2.0)	225	18	1/2 (13)
		Flat & Horizontal	125 (3.2)	275	19	5/8 (16)
		Flat & Horizontal	175 (4.4)	325	20	3/4 (19)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

## PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.