

Select 720C Low Mn

Carbon Steel / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Superb weldability, designed for ease of welding in all positions
- Total manganese (Mn) content is significantly reduced compared to standard E71T-1/-9 electrodes.
- Mechanical properties meet industry requirements and exceed competitive low manganese type wires of same AWS classification.
- Intended for use with 100% CO₂ shielding gas.
- Excels in general fabrication, structural steel, and shipbuilding applications where ASTM A36, A515-gr 70, and A516-gr 70 type materials are being used.


CONFORMANCES

AWS A5.20	E71T-1C E71T-9C
ASME SFA 5.20	E71T-1C E71T-9C
AWS A5.36	E71T1-C1A2-CS1

DIAMETERS (in [mm])

0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

POSITIONS



SHIELDING GAS

100% CO₂
Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si	V
100%CO ₂	0.04	0.05	0.23	0.30	0.00	0.40	0.007	0.011	0.40	0.01

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ 0°F (-20°C) ft-lb (J)	CVN @ -20°F (-30°C) ft-lb (J)
100%CO ₂	79 (545)	71 (490)	26	As-Welded	-	56 (76)	54 (73)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	100% CO2	All Positions	200 (5.1)	145	24	1/2 - 5/8 (13 - 16)
		All Positions	235 (6.0)	160	25	1/2 - 5/8 (13 - 16)
		All Positions	300 (7.6)	185	27	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	215	28	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	29	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	100% CO2	All Positions	170 (4.3)	155	24	5/8 - 3/4 (16 - 19)
		All Positions	200 (5.1)	175	25	5/8 - 3/4 (16 - 19)
		All Positions	250 (6.4)	225	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	310 (7.9)	250	28	3/4 - 1 (19 - 25)
		Flat & Horizontal	395 (10.0)	280	29	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	100% CO2	All Positions	125 (3.2)	165	24	5/8 - 3/4 (16 - 19)
		All Positions	150 (3.8)	195	25	5/8 - 3/4 (16 - 19)
		All Positions	185 (4.7)	225	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	265 (6.7)	280	28	3/4 - 1 (19 - 25)
		Flat & Horizontal	325 (8.3)	320	29	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

APPROVALS

Agency	Approval	Shielding Gas	Diameter(s) in (mm)
CWB CSA W48-23	E491T1-C1A3-CS1-H8	C1 (100%CO2)	0.045 (1.2) - 1/16 (1.6)

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.