

Select 720HP H4

Carbon Steel / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Designed for single & multiple pass welding of carbon steels, such as ASTM A36, A285, A515-Gr 70, & A516-Gr 70.
- Developed for low hydrogen deposits utilizing 75-80% Ar/balance CO₂ sheilding gas.
- Microalloying and slag adjustments provide enhanced CVN toughness values at lower than required classification temperatures.
- Well suited for structural welding and general fabrication.
- A good choice for fine grained, high toughness steels, such as ASTM A572 and A633.


CONFORMANCES

AWS A5.20	E71T-12M-JH4
AWS A5.29	E81T1-GM-H4

DIAMETERS (in [mm])

0.035 (0.9), 0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

POSITIONS



SHIELDING GAS

75-80%Ar/Balance

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si	V
75%Ar / 25%CO ₂	0.06	0.04	0.022	1.35	<0.01	0.40	0.01	0.01	0.36	0.02

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -20°F (-30°C) ft-lb (J)	CVN @ -40°F (-40°C) ft-lb (J)	CVN @ -60°F (-50°C) ft-lb (J)
75%Ar / 25%CO ₂	87 (600)	76 (524)	27	As-Welded	-	111 (151)	95 (129)	65 (88)



Revision: 12/15/2024

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • www.Select-SAI.com

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	75% Ar/25% CO2	All-Position	275 (7.0)	120	22	1/2 - 5/8 (13 - 16)
		All-Position	320 (8.1)	135	23	1/2 - 5/8 (13 - 16)
		All-Position	420 (10.7)	160	25	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	465 (11.8)	180	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	570 (14.5)	200	28	5/8 - 3/4 (16 - 19)
0.045 (1.2 mm)	75% Ar/25% CO2	All-Position	200 (5.1)	145	22	1/2 - 5/8 (13 - 16)
		All-Position	235 (6.0)	160	23	1/2 - 5/8 (13 - 16)
		All-Position	300 (7.6)	185	25	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	215	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	28	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	75% Ar/25% CO2	All-Position	170 (4.3)	155	22	5/8 - 3/4 (16 - 19)
		All-Position	200 (5.1)	175	23	5/8 - 3/4 (16 - 19)
		All-Position	250 (6.4)	225	25	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	310 (7.9)	250	26	3/4 - 1 (19 - 25)
		Flat & Horizontal	395 (10.0)	280	28	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO2	All-Position	125 (3.2)	165	22	5/8 - 3/4 (16 - 19)
		All-Position	150 (3.8)	195	23	5/8 - 3/4 (16 - 19)
		All-Position	185 (4.7)	225	25	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	265 (6.7)	280	26	3/4 - 1 (19 - 25)
		Flat & Horizontal	325 (8.3)	320	28	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

APPROVALS

Agency	Approval	Shielding Gas	Diameter(s) in (mm)
ABS	4YSA H5	M21 (75%Ar / 25%CO2)	0.035 (0.9) - 1/16 (1.6)
DNV	IV YMS (H5)	M21 (75%Ar / 25%CO2)	0.035 (0.9) - 1/16 (1.6)

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.