

Select 80C-B2

Low Alloy / Gas Shielded / Metal Cored

PRODUCT DATA SHEET

FEATURES

- Select 80C-B2 is intended for single and multiple pass welding of certain chrome-moly steels.
- Intended to weld materials such as ASTM A335-11 pipe and A387 Grade 11 plate. These materials are air hardening in nature, therefore both preheat and postweld heat treatments are necessary.
- When properly applied, the weld metal should deliver the same creep resistance and high temperature properties of the base metals.

CONFORMANCES

AWS A5.28	E80C-B2
ASME SFA 5.28	E80C-B2

DIAMETERS [in (mm)]

0.045 (1.2), 0.052 (1.3)

POSITIONS



SHIELDING GAS

75-95%Ar/Balance CO₂, 95-98% Ar / 2-5% O₂
Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	P	S	Si	V
98%Ar / 2%O ₂	0.06	1.16	0.04	0.65	0.56	0.010	0.010	0.43	0.004

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
98%Ar / 2%O ₂	87 (600)	70 (483)	23	PWHT	1150F for



Revision: 9/16/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • www.Select-SAI.com

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO2	Flat & Horizontal	260 (6.6)	200	25	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	305 (7.7)	220	26	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	360 (9.1)	240	27.5	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	405 (10.3)	255	29	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	75% Ar/25% CO2	Flat & Horizontal	235 (6.0)	215	25	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	315 (8.0)	260	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	330 (8.4)	275	27.5	3/4 - 1 (19 - 25)
		Flat & Horizontal	345 (8.8)	295	29	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

Welding parameters are for 75% Ar /25% CO2, at higher levels of argon the voltage should be gradually decreased: ½-1 volt for 85% Ar/15% CO2, 1-1 ½ volts for 90% Ar/10% CO2, and 1-2 volts for 95% Ar/5% CO2 & 98% Ar/2% O2.

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.