

Select 81-A1

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Designed for flat or horizontal welding in single or multiple pass applications.
- Addition of ~0.5 wt% molybdenum (Mo) provides increased high temperature strength compared to standard carbon steel electrodes.
- Commonly used in fabrication and erection of boilers and pressure vessels.
- Applications include the welding of C-Mo steel base metals (ASTM A161, A204, A302 Gr. A plate, and A335-P1 pipe).

CONFORMANCES

AWS A5.29

E80T1-A1C

DIAMETERS [in (mm)]

5/64 (2.0), 3/32 (2.4)

POSITIONS



SHIELDING GAS

100% CO₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

Shielding Gas	C	Mn	Mo	P	S	Si
100%CO ₂	0.05	0.52	0.51	0.010	0.012	0.33

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
100%CO ₂	88 (607)	75 (517)	24	PWHT	1150°F for 1 Hr



Revision: 9/20/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • www.Select-SAI.com

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
5/64 (2.0 mm)	100% CO ₂	Flat & Horizontal	145 (3.7)	280	25	1 (25)
		Flat & Horizontal	190 (4.8)	320	27	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	230 (5.8)	365	29	1 - 1 1/4 (25 - 32)
3/32 (2.4 mm)	100% CO ₂	Flat & Horizontal	120 (3.0)	275	25	1 1/4 (32)
		Flat & Horizontal	150 (3.8)	335	27	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	165 (4.2)	400	29	1 1/4 - 1 1/2 (32 - 38)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.