

# Select 810-B6

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Intended for welding of certain chromium-molybdenum steels where a weld deposit of 5% chromium and 0.5% molybdenum is required.
- Smooth, stable arc transfer with low spatter emission.
- Greater tolerance of mill scale and rust.
- Specially formulated for welding tube, pipe, and plate subjected to high temperature service, such as A213-T5 and A335-P5.

## CONFORMANCES


AWS A5.29

E81T1-B6M-H8

## DIAMETERS (in (mm))

0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

## POSITIONS



## SHIELDING GAS

75-80% Ar/Balance CO2

Flow Rate: 40 - 50 CFM

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si
75%Ar / 25%CO2	0.09	5.31	0.03	0.47	0.56	0.02	0.007	0.013	0.24

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ 70°F (21°C) ft-lb (J)
75%Ar / 25%CO2	93 (641)	75 (515)	21	PWHT	1375°F for 2 hrs	70.5 (96)



Revision: 12/2/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • [www.Select-Arc.com](http://www.Select-Arc.com)

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO2	All Positions	200 (5.1)	145	22	1/2 - 5/8 (13 - 16)
		All Positions	235 (6.0)	160	23	1/2 - 5/8 (13 - 16)
		All Positions	300 (7.6)	185	25	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	215	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	28	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	75% Ar/25% CO2	All Positions	170 (4.3)	155	22	5/8 - 3/4 (16 - 19)
		All Positions	200 (5.1)	175	23	5/8 - 3/4 (16 - 19)
		All Positions	250 (6.4)	225	25	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	310 (7.9)	250	26	3/4 - 1 (19 - 25)
		Flat & Horizontal	395 (10.0)	280	28	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO2	All Positions	125 (3.2)	165	22	5/8 - 3/4 (16 - 19)
		All Positions	150 (3.8)	195	23	5/8 - 3/4 (16 - 19)
		All Positions	185 (4.7)	225	25	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	265 (6.7)	280	26	3/4 - 1 (19 - 25)
		Flat & Horizontal	325 (8.3)	320	28	3/4 - 1 (19 - 25)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

## PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.