# Select 85-B2L

Low Alloy / Gas Shielded / Flux Cored

### **FEATURES**

- Intended for welding of certain 1.25% Cr and 0.5% Mo steel plate and pipe requiring lower carbon levels in the weld deposit
- Great choice for welding A335-P11 pipe and A213-T11 or A213-T22 tube in the as-welded condition or in applications where low hardness is required.
- Typical applications include construction of boilers, heat exchangers, and pressure vessels.

# DIAMETERS (in (mm))

1/16 (1.6)

#### POSITIONS



# SHIELDING GAS

100% CO2 Flow Rate: 40 - 50 CFH

#### POLARITY

Direct Current Electrode Positive (DCEP)

# TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	С	Cr	Mn	Мо	Р	S	Si
100%CO2	0.02	1.41	0.81	0.50	0.008	0.013	0.35

# **TYPICAL MECHANICAL PROPERTIES**

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
100%CO2	89 (614)	77 (531)	24	PWHT	1275°F for 1 hr

# **RECOMMENDED WELDING PARAMETERS \*\***

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
1/16 (1.6 mm)		Flat & Horizontal	250 (6.4)	265	25	3/4 (19)
	100% CO2	Flat & Horizontal	280 (7.1)	290	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	315 (8.0)	315	29	3/4 - 1 (19 - 25)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

\*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "allposition" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use

# CONFORMANCES

AWS A5.29

E80T5-B2LC

# PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum \*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

#### **STORAGE AND HANDLING**

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com