

Low Alloy / Flux Shielded / Submerged Arc

PRODUCT DATA SHEET

FEATURES

- Intended for single and multiple pass welding of base metal with similar Cr-Mo composition.
- Higher deposition rates than solid wire at the same current level
- Exhibits a broader and shallower bead profile than when using solid wire, reducing the tendency for burn through
- Capable of running directly over root passes with proper procedure – eliminating requirement for a hot pass
- Easy slag removal reduces post weld cleanup time
- Typical applications include welding of 1½ Cr ½ Mo pipe and plate like ASTM A335-11 pipe and A387 Grade 11 plate, All welds need to be post weld heat treated.
- Arcflux BF-10MW is the recommended flux, although other neutral fluxes with high basicity can be used as well.

CONFORMANCES

AWS A5.23 ECB2

F8P2-ECB2-B2

ASME SFA 5.23 ECB2

F8P2-ECB2-B2

DIAMETERS (in (mm))

5/32 (4.0)

POSITIONS



FLUX

Arcflux BF-10MW

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Flux	С	Cr	Cu	Mn	Мо	Р	S	Si
ARCFLUX BF-10 MW	0.06	1.36	0.06	1.06	0.48	0.021	0.013	0.47

TYPICAL MECHANICAL PROPERTIES

Flux	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -20°F (-30°C) ft-lb (J)
ARCFLUX BF-10 MW	90 (621)	75 (517)	27	PWHT	1275°F for 1 hr	92 (125)



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS **

Diameter in (mm)	Flux	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
5/32 (4.0 mm)	ARCFLUX BF-10 MW	Flat & Horizontal	50 (1.3)	450	30	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	65 (1.7)	550	31	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	80 (2.0)	650	32	1 - 1 1/4 (25 - 32)

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

^{*} WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance
**The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "allposition" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

^{*}Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.