# Select EM12KS

Carbon Steel / Flux Shielded / Submerged Arc

#### PRODUCT DATA SHEET

## **FEATURES**

#### Intended for single and multiple pass welding of carbon and certain low alloy steels, and can be substituted anywhere that a solid EM12K electrode is used.

- Produces a weld deposit chemistry similar to EM12K solid wire electrodes.
- Higher deposition rates than solid wire when run at the same current level.
- Exhibits a broader and shallower bead profile than when using solid wire, reducing the tendency for burn through.
- Capable of running directly over root passes with proper procedure - eliminating requirement for a hot pass.
- Easy slag removal reduces post weld cleanup time
- Arcflux BF-10MW is the recommended flux, although other active and neutral fluxes can be used in place of this.

# **DIAMETERS** (in (mm))

5/64 (2.0), 3/32 (2.4), 1/8 (3.2), 5/32 (4.0)

## POSITIONS



## FLUX

Arcflux BF-10MW, Arcflux BF-3.5, Arcflux BF-1, Arcflux BF-5.1

## POLARITY

Direct Current Electrode Positive (DCEP)

# **TYPICAL WELD DEPOSIT CHEMISTRY (WT%)**

Flux	С	Cu	Mn	Р	S	Si
ARCFLUX BF 3.5	0.08	0.07	1.72	0.021	0.011	0.58
ARCFLUX BF 5.1	0.08	0.04	1.31	0.022	0.015	0.41
ARCFLUX BF-1	0.07	0.10	1.39	0.026	0.019	0.66
ARCFLUX BF-10 MW	0.09	0.08	1.30	0.014	0.008	0.36



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products

Revision: 1/17/2025

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com

## CONFORMANCES

ASME SFA 5.17

EC1
F7A2-EC1-H8 (ARCFLUX BF-1)
F7A6-EC1 (ARCFLUX BF 5.1)
F7A6-EC1-H8 (ARCFLUX BF 3.5)
F7A8-EC1-H8 (ARCFLUX BF-10 MW)

	AWS A5.17	EC1
'n		F7A2-EC1-H8 (ARCFLUX BF-1)
		F7A6-EC1 (ARCFLUX BF 5.1)
		F7A6-EC1-H8 (ARCFLUX BF 3.5)
t		F7A8-EC1 (ARCFLUX BF-10 MW)
e.		
h	AWS D1.8	3/32 in (2.4 mm), (ARCFLUX BF 3.5)
		3/32 in (2.4 mm), (ARCFLUX BF-10 MW)

5/32 in (4.0 mm), (ARCFLUX BF 3.5)

## **TYPICAL MECHANICAL PROPERTIES**

Flux	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -20°F (-30°C) ft-lb (J)	CVN @ -60°F (-50°C) ft-lb (J)	CVN @ -80°F (-60°C) ft-lb (J)
ARCFLUX BF 3.5	87 (600)	71 (490)	24	As-Welded	-	-	59 (80)	-
ARCFLUX BF 5.1	77 (531)	62 (428)	31	As-Welded	-	-	78 (106)	-
ARCFLUX BF-1	84 (579)	70 (483)	24	As-Welded	-	35 (47)	-	-
ARCFLUX BF-10 MW	79 (545)	68 (469)	32	As-Welded	-	170 (231)	-	122 (165)

## **RECOMMENDED WELDING PARAMETERS \*\***

Diameter in (mm)	Flux	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
		Flat & Horizontal	100 (2.5)	200	27.0	3/4 - 1 (19 - 25)
5/64 (2.0 mm)	ARCFLUX BF-10 MW	Flat & Horizontal	180 (4.6)	300	27.5	3/4 - 1 (19 - 25)
		Flat & Horizontal	260 (6.6)	400	28.0	3/4 - 1 (19 - 25)
3/32 (2.4 mm) AR(		Flat & Horizontal	60 (1.5)	250	27.5	1 - 1 1/4 (25 - 32)
	ARCFLUX BF-10 MW	Flat & Horizontal	85 (2.2)	350	28.0	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	130 (3.3)	450	29.0	1 - 1 1/4 (25 - 32)
1/8 (3.2 mm)		Flat & Horizontal	55 (1.4)	350	28.5	1 - 1 1/4 (25 - 32)
	ARCFLUX BF-10 MW	Flat & Horizontal	75 (1.9)	450	29.5	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	100 (2.5)	550	30.5	1 - 1 1/4 (25 - 32)
5/32 (4.0 mm)	ARCFLUX BF-10 MW	Flat & Horizontal	50 (1.3)	450	30.0	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	65 (1.7)	550	31.0	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	80 (2.0)	650	32.0	1 - 1 1/4 (25 - 32)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance \*\*The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

The recommended parameters are for Arcflux BF-10MW; parameters may vary with different fluxes. For parameter recommendations with different fluxes, please call our technical support team at 1-800-341-5215.

## **APPROVALS**

Agency	Approval	Flux	Diameter(s) in (mm)	
ABS	4YM H5	ARCFLUX BF-10 MW	1/16 (1.6) - 3/16 (4.8)	
CWB CSA W48-23	E49A5-EC1-H8	ARCFLUX BF 3.5	3/32 (2.4) - 3/16 (4.8)	
	F49A3-EC1-H8	ARCFLUX BF-1	5/64 (2.0) - 5/32 (4.0)	
	F49A5-EC1-H8	ARCFLUX BF-10 MW	5/64 (2.0) - 5/32 (4.0)	

# PACKAGING [lbs [kgs]]

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## **STORAGE AND HANDLING**

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products. 600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use