

Select ER18CrCb

Stainless Steel / Gas Shielded / Solid

PRODUCT DATA SHEET

FEATURES

- Nominally ~18 wt% Cr with columbium (Cb), also known as niobium (Nb), as the stabilizing element to prevent weld metal sensitization.
- Nb stabilization promotes enhanced weldability on components where cleanliness can be an issue (i.e. excessive debris, oil, etc.).
- Unique manufacturing techniques provide enhanced arc stability and stable feeding.
- Applications for this alloy type include ferritic stainless steel exhaust system components, converters, mufflers, and tubing of similar composition where heat and corrosion resistance are necessary.


CONFORMANCES

ISO 14343-A	18 L Nb
AWS A5.9	G 18 L Nb

DIAMETERS (in [mm])

0.035 (0.9), 0.040 (1.0), 0.045 (1.2)

POSITIONS



SHIELDING GAS

Ar + 0.5-5% CO₂, Ar + 0.5-3% O₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	N	Nb	Ni	P	S	Si
Argon	0.02	18.20	0.09	0.40	0.28	0.015	0.45	0.28	0.023	0.005	0.45



Revision: 4/5/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • www.Select-SAI.com

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	98% Ar/2% O ₂	Flat & Horizontal	315 (8.0)	135	20	1/2 (13)
		Flat & Horizontal	500 (12.7)	170	22	1/2 (13)
		Flat & Horizontal	650 (16.5)	220	23	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	780 (19.8)	250	25	5/8 - 3/4 (16 - 19)
0.040 (1.0 mm)	98% Ar/2% O ₂	Flat & Horizontal	295 (7.5)	190	20	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	220	21	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	525 (13.3)	255	23	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	630 (16.0)	280	25	5/8 - 3/4 (16 - 19)
0.045 (1.2 mm)	98% Ar/2% O ₂	Flat & Horizontal	280 (7.1)	225	20	5/8 (16)
		Flat & Horizontal	350 (8.9)	245	21	5/8 (16)
		Flat & Horizontal	400 (10.2)	265	23	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	475 (12.1)	300	25	5/8 - 3/4 (16 - 19)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.