

Select 101 SR

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Intended for single and multiple pass welding of quenched and tempered steels that require a postweld stress relief.
- Excellent high strength properties in the as-welded condition.
- This electrode is designed for 75-80% argon – balance carbon dioxide; the use of 100 percent carbon dioxide should be avoided.
- The rutile based fast freezing slag facilitates welding in all positions, with moderate slag volume and easy removal.
- Select 101-SR is designed to weld oil field components that require a postweld stress relief. However, it is not designed for postweld quench and temper treatments. Select 4130LN should be used if the weldment is to receive postweld quench and temper.
- Also be used to weld high strength, low alloy steels where 100 ksi minimum tensile strength and excellent toughness are required in the as welded condition.

CONFORMANCES

AWS A5.29

E101T1-GM-H4


ASME SFA 5.29

E101T1-GM-H4

DIAMETERS [in (mm)]

0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

POSITIONS



SHIELDING GAS

75-80%Ar/Balance CO2

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Mn	Mo	Ni	P	S	Si
75%Ar / 25%CO2	0.06	1.40	0.35	0.85	0.010	0.007	0.30

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ -20°F (-30°C) ft-lb (J)	CVN @ -40°F (-40°C) ft-lb (J)
75%Ar / 25%CO2	108 (745)	99 (683)	21	As-Welded	-	41 (56)	33 (45)
75%Ar / 25%CO2	103 (710)	94 (648)	22	PWHT	1150F for 1 Hr	36 (49)	27 (37)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO2	All Positions	200 (5.1)	145	23	1/2 - 5/8 (13 - 16)
		All Positions	235 (6.0)	160	24	1/2 - 5/8 (13 - 16)
		All Positions	300 (7.6)	185	26	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	215	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	29	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	75% Ar/25% CO2	All Positions	170 (4.3)	155	23	5/8 - 3/4 (16 - 19)
		All Positions	200 (5.1)	175	24	5/8 - 3/4 (16 - 19)
		All Positions	250 (6.4)	225	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	310 (7.9)	250	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	395 (10.0)	280	29	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO2	All Positions	125 (3.2)	165	23	5/8 - 3/4 (16 - 19)
		All Positions	150 (3.8)	195	24	5/8 - 3/4 (16 - 19)
		All Positions	185 (4.7)	225	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	265 (6.7)	280	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	325 (8.3)	320	29	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

APPROVALS

Agency	Approval	Shielding Gas	Diameter(s) in (mm)
ABS	E101T1-GM	M21 (75%Ar / 25%CO2)	0.045 (1.2) - 1/16 (1.6)

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.