

# Select 110-K3

Low Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

## FEATURES

- Intended for single and multiple pass welding of structural steel and fabrications utilizing high strength, low alloy steels, such as HY-100 and ASTM A514 type alloys.
- The arc transfer mode is a smooth, small to medium ball transfer that produces minimal spatter.
- Slag removes easily with no residual slag where minimal clean-up is required.
- Typical applications include low temperature storage tanks, offshore drilling rigs, shipbuilding, and construction machinery where excellent low-temperature toughness is required.

## CONFORMANCES

AWS A5.29	E110T1-K3C
ASME SFA 5.29	E110T1-K3C

## DIAMETERS (in [mm])

0.045 (1.2), 0.052 (1.3), 1/16 (1.6), 5/64 (2.0), 3/32 (2.4)

## POSITIONS



## SHIELDING GAS

100% CO<sub>2</sub>

Flow Rate: 40 - 50 CFM

## POLARITY

Direct Current Electrode Positive (DCEP)

## TYPICAL WELD DEPOSIT CHEMISTRY [WT%]

Shielding Gas	C	Cr	Mn	Mo	Ni	P	S	Si	V
100%CO <sub>2</sub>	0.07	0.04	1.54	0.49	2.29	0.009	0.010	0.34	0.02

## TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ 0°F (-20°C) ft-lb (J)
100%CO <sub>2</sub>	116 (800)	105 (724)	19	As-Welded	-	38 (52)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	100% CO2	Flat & Horizontal	250 (6.4)	175	24	5/8 (16)
		Flat & Horizontal	340 (8.6)	205	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	440 (11.2)	235	29	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	100% CO2	Flat & Horizontal	245 (6.2)	210	24	3/4 - 1 (19 - 25)
		Flat & Horizontal	250 (6.4)	310	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	280 (7.1)	395	29	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	100% CO2	Flat & Horizontal	235 (6.0)	245	24	3/4 (19)
		Flat & Horizontal	280 (7.1)	275	27	3/4 - 1 (19 - 25)
		Flat & Horizontal	325 (8.3)	320	29	3/4 - 1 (19 - 25)
5/64 (2.0 mm)	100% CO2	Flat & Horizontal	145 (3.7)	280	25	1 (25)
		Flat & Horizontal	190 (4.8)	320	27	1 - 1 1/4 (25 - 32)
		Flat & Horizontal	230 (5.8)	365	29	1 - 1 1/4 (25 - 32)
3/32 (2.4 mm)	100% CO2	Flat & Horizontal	120 (3.0)	275	25	1 1/4 (32)
		Flat & Horizontal	150 (3.8)	335	27	1 1/4 - 1 1/2 (32 - 38)
		Flat & Horizontal	165 (4.2)	400	29	1 1/4 - 1 1/2 (32 - 38)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

## PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.