

Select Var36

Nickel Alloy / Gas Shielded / Flux Cored

PRODUCT DATA SHEET


FEATURES

- Designed for welding various low thermal expansion alloys
- Exceptional arc stability in all positions
- Deposit chemistry meets requirements of ASTM F1684
-

DIAMETERS (in (mm))

0.045" ()

POSITIONS



SHIELDING GAS

75-80% Ar / Balance CO₂

Flow Rate: 40 - 50 CFM

POLARITY

DCEP

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Fe	Mn	Ni	P	S	Si
75%Ar / 25%CO ₂	0.02	Bal.	0.30	36.5	0.003	0.001	0.07

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO ₂	Vertical Up	260 (6.6)	180	22	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	350 (8.9)	225	23	1/2 - 5/8 (13 - 16)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 9/16/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com