

SelectAlloy 312-C

Stainless Steel / Gas Shielded / Metal Cored

PRODUCT DATA SHEET

FEATURES

- This alloy types resulting two phase microstructure, even with considerable dilution by austenite-forming elements, promotes weld metal crack resistance and fissures.
- Metal cored benefits include the ability to successfully bridge gaps when part fit up is not as designed, higher travel speeds with subsequent lower heat inputs at equal amperages, and ability to join thin materials.
- Applications include welding dissimilar metals such as carbon steel to stainless steel, particularly those grades high in nickel, and welding of castings of similar composition.

CONFORMANCES

AWS A5.22	EC312
ASME SFA 5.22	EC312

DIAMETERS (in [mm])

0.035 (0.9), 0.045 (1.2), 1/16 (1.6)

POSITIONS



SHIELDING GAS

Ar + 0.5-5% CO₂, Ar + 0.5-3% O₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si
98%Ar / 2%O ₂	0.08	29.50	0.16	1.83	0.09	9.69	0.022	0.007	0.36
Ferrite	Result								
WRC 1992	65 FN								

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
98%Ar / 2%O ₂	114 (786)	87 (600)	24	As-Welded	-



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	98% Ar/2% O ₂	Flat & Horizontal	450 (11.4)	170	21	1/2 (13)
		Flat & Horizontal	515 (13.1)	185	23	1/2 (13)
		Flat & Horizontal	560 (14.2)	200	24	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	655 (16.6)	205	26	1/2 - 5/8 (13 - 16)
0.045 (1.2 mm)	98% Ar/2% O ₂	Flat & Horizontal	325 (8.3)	220	22	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	235	23	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	420 (10.7)	250	24	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	500 (12.7)	270	26	5/8 - 3/4 (16 - 19)
1/16 (1.6 mm)	98% Ar/2% O ₂	Flat & Horizontal	225 (5.7)	265	21	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	300 (7.6)	305	23	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	330 (8.4)	335	24	3/4 - 1 (19 - 25)
		Flat & Horizontal	375 (9.5)	350	26	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.