# SelectAlloy 316LMn-C Mod

Stainless Steel / Gas Shielded / Metal Cored

PRODUCT DATA SHEET

## **FEATURES**

- Similar chemical composition to EC316LMn with modifiactions to keep ferrite ultra low
- Ideal for welding applications where ultra low ferrite numbers are required

#### CONFORMANCES

**AWS A5.22** 

**ECG** 

## **DIAMETERS (in (mm))**

0.045 (1.2)

#### **POSITIONS**



#### **SHIELDING GAS**

Ar + 0.5-3% CO2, Ar + 0.5-3% O2

Flow Rate: 40 - 50 CFH

### **POLARITY**

Direct Current Electrode Positive (DCEP)

## **TYPICAL WELD DEPOSIT CHEMISTRY (WT%)**

Shielding Gas	С	Cr	Cu	Mn	Мо	N	Ni	P	S	Si	
Argon	0.03	18	0.40	4	2	0.20	13	0.02	<0.001	0.5	

#### **TYPICAL MECHANICAL PROPERTIES**

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
98%Ar / 2%O2	94 (650)	61 (418)	38	As-Welded	-

## **RECOMMENDED WELDING PARAMETERS \*\***

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	98% Ar/2% O2	Flat & Horizontal	325 (8.3)	220	22	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	235	23	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	420 (10.7)	250	24	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	500 (12.7)	270	26	5/8 - 3/4 (16 - 19)

<sup>\*</sup> WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

<sup>\*\*</sup>The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

## PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## **STORAGE AND HANDLING**

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.