

SelectAlloy 317L

Stainless Steel / Gas Shielded / Flux Cored

PRODUCT DATA SHEET

FEATURES

- Low C, < 0.04 wt%, minimizes carbide precipitation (sensitization) which makes the weld metal more resistant to intergranular corrosion.
- The addition of Mo improves resistance to pitting and crevice corrosion compared to type 308 stainless steel with increased resistance compared to type 316 due to the nominal ~1 % increase (Mo).
- Produces a finely rippled, equal legged, and well washed bead geometry in both 100% CO₂ or 75-80% Ar/balance CO₂ shielding gas
- Smooth arc transfer and self-releasing slag that peels freely to ensure that clean up time is minimized.
- Applications for this alloy type include welding components of similar composition or multilayer classing applications in severely corrosive environments, where crevice and pitting corrosion are of concern.

CONFORMANCES

AWS A5.22

E317LT0-1

E317LT0-4

ASME SFA 5.22

E317LT0-1

E317LT0-4

DIAMETERS (in [mm])

0.035 (0.9), 0.045 (1.2), 1/16 (1.6)

POSITIONS



SHIELDING GAS

75-80% Ar + Balance CO₂, 100% CO₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	Bi	C	Cr	Cu	Mn	Mo	Ni	P	S	Si	WRC-1992 Ferrite
100%CO ₂	>0.002	0.03	19.40	0.17	1.00	3.15	11.90	0.02	0.01	0.60	12
75%Ar / 25%CO ₂	>0.002	0.03	19.50	0.18	1.15	3.16	12.30	0.02	0.01	0.70	12

Bismuth is not intentionally added and levels are not known to be greater than 0.002 (WT%)

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp
100%CO ₂	88 (607)	64 (441)	35	As-Welded	-
75%Ar / 25%CO ₂	89 (614)	65 (448)	35	As-Welded	-



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	75% Ar/25% CO2	Flat & Horizontal	375 (9.5)	120	25	1/2 (13)
		Flat & Horizontal	590 (15.0)	150	28	1/2 (13)
		Flat & Horizontal	690 (17.5)	165	30	5/8 (16)
0.045 (1.2 mm)	75% Ar/25% CO2	Flat & Horizontal	210 (5.3)	145	24	1/2 (13)
		Flat & Horizontal	390 (9.9)	185	28	5/8 (16)
		Flat & Horizontal	550 (14.0)	235	32	3/4 (19)
1/16 (1.6 mm)	75% Ar/25% CO2	Flat & Horizontal	155 (3.9)	180	24	5/8 (16)
		Flat & Horizontal	235 (6.0)	220	27	3/4 (19)
		Flat & Horizontal	300 (7.6)	265	31	1 (25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

Parameters were established in 75% Ar/25% CO2. Raise by 1-1.5 volts when using 100% CO2.

PACKAGING [lbs (kgs)]

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.