

SelectSuper NC3

Carbon Steel / Gas Shielded / Solid

PRODUCT DATA SHEET

FEATURES

- A carbon steel, solid “MIG wire” electrode with no copper coating, for gas shielded arc welding.
- Moderate levels of manganese and silicon compared to 70S-6 electrodes reduces silicate slag on weld deposit which minimizes postweld cleanup.
- Reduced copper fumes, no copper flaking, crisp arc starts, and a reduction of spatter can all be observed as a result of a bare, copper free wire.
- Recommended shielding gases are 75-95% argon/balance carbon dioxide, 95-98% argon/balance oxygen, and 100% carbon dioxide.
- Intended for welding carbon steels, such as ASTM A36, A515, A516, and A572.
- Smaller diameters (1/16” or smaller) can be pulse welded in all positions.
- The versatility of a slag free solid wire makes this ideal for general fabrication, structural steel welds, and thin section applications, such as automotive components and hot water heaters with minor amounts of mill scale.

CONFORMANCES


AWS A5.18

ER70S-3

DIAMETERS (in (mm))

0.035 (0.9), 0.045 (1.2), 0.052 (1.3), 1/16 (1.6)

POSITIONS



SHIELDING GAS

100% CO₂, 75-95% Ar/Balance CO₂, 95-98% Ar/Balance O₂

Flow Rate: 40 - 50 CFM

POLARITY

DCEP

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Cu	Mn	Mo	Ni	P	S	Si	V
N/A	0.09	0.02	0.01	1.20	<0.01	0.01	0.01	0.01	0.55	0.01

TYPICAL MECHANICAL PROPERTIES

Shielding Gas	Tensile Strength ksi (MPa)	Yield Strength ksi (MPa)	Elongation (%)	Weld Condition	PWHT Temp	CVN @ 0°F (-20°C) ft-lb (J)
100%CO ₂	77 (531)	61 (421)	30	As-Welded	-	95 (129)
90%Ar / 10%CO ₂	79 (545)	65 (448)	29	As-Welded	-	111 (151)



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	90% Ar/10% CO2	Flat & Horizontal	380 (9.7)	175	25	3/8 - 5/8 (10 - 16)
		Flat & Horizontal	450 (11.4)	230	27	3/8 - 5/8 (10 - 16)
		Flat & Horizontal	550 (14.0)	250	29	1/2 - 3/4 (13 - 19)
		Flat & Horizontal	625 (15.9)	275	30	1/2 - 3/4 (13 - 19)
0.045 (1.2 mm)	90% Ar/10% CO2	Flat & Horizontal	310 (7.9)	240	26	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	375 (9.5)	275	28	1/2 - 5/8 (13 - 16)
		Flat & Horizontal	450 (11.4)	325	29	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	550 (14.0)	375	30	5/8 - 3/4 (16 - 19)
0.052 (1.3 mm)	90% Ar/10% CO2	Flat & Horizontal	260 (6.6)	275	26	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	355 (9.0)	325	28	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	450 (11.4)	375	29	3/4 - 1 (19 - 25)
		Flat & Horizontal	525 (13.3)	425	30	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	90% Ar/10% CO2	Flat & Horizontal	190 (4.8)	300	27	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	245 (6.2)	360	28	5/8 - 3/4 (16 - 19)
		Flat & Horizontal	290 (7.4)	420	29	3/4 - 1 (19 - 25)
		Flat & Horizontal	330 (8.4)	475	30	3/4 - 1 (19 - 25)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

*For higher argon blends such as 98%Ar/2%O2, decrease the voltage by 1 - 3 volts. For higher levels of CO2, increase voltage by 1-3 volts.

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.