

# SelectWear 42-FCG

Hardsurfacing / Gas Shielded / Hardfacing

PRODUCT DATA SHEET

## FEATURES

- Deposits a low alloy, martensitic steel designed for low to medium stress metal-to-metal wear
- Multiple layers can be deposited with proper welding procedure
- Applications include: Earthmoving idlers and rollers, wheels (mine cars, cranes etc.), overlay welds that have joined abrasion resistant plates such as AR400

## DIAMETERS (in [mm])

0.045 (1.2), 1/16 (1.6)

## POSITIONS



## SHIELDING GAS

100% CO<sub>2</sub>, 75%Ar / 25% CO<sub>2</sub>

Flow Rate: 40 - 50 CFM

## POLARITY

Direct Current Electrode Positive (DCEP)

## HARDNESS

3 layers: 40-46 HRC HRC

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO <sub>2</sub>	Flat & Horizontal	375 (9.5)	250	27	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO <sub>2</sub>	Flat & Horizontal	275 (7.0)	300	28	3/4 - 1 1/4 (19 - 32)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

For Welding in 100% CO<sub>2</sub>, increase by 1 - 1.5 volts

## PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.