

SelectWear 42-MCG

Hardsurfacing / Gas Shielded / Metal Cored

PRODUCT DATA SHEET

FEATURES

- Deposits a low alloy, martensitic steel designed for low to medium stress metal to metal wear
- Multiple layers can be deposited with proper welding procedure
- Applications include: Earthmoving idlers and rollers, Wheels (Mine cars, cranes, etc.), Overlay welds that have joined abrasion resistant plates such as AR400

DIAMETERS (in [mm])

0.035 (0.9), 0.045 (1.2), 1/16 (1.6), 5/64 (2.0)

POSITIONS



SHIELDING GAS

100% CO₂, 75-90% Ar/Balance CO₂

Flow Rate: 40 - 50 CFH

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

3 layers: 40 - 46 HRC

RECOMMENDED WELDING PARAMETERS **

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.035 (0.9 mm)	75% Ar/25% CO ₂	Flat & Horizontal	500 (12.7)	200	26	1/2 - 1 (13 - 25)
0.045 (1.2 mm)	75% Ar/25% CO ₂	Flat & Horizontal	400 (10.2)	250	27	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO ₂	Flat & Horizontal	275 (7.0)	300	28	3/4 - 1 1/4 (19 - 32)
5/64 (2.0 mm)	75% Ar/25% CO ₂	Flat & Horizontal	225 (5.7)	350	28	3/4 - 1 1/4 (19 - 32)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

**The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

For Welding in 100% CO₂, increase by 1 - 1.5 volts

At higher levels of argon the voltage should be gradually decreased; 0.5-1 volt for 85% Ar/15% CO₂, 1-1.5 volts for 90% Ar/10% CO₂

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.