SelectWear 420-MCG

Hardsurfacing / Gas Shielded / Metal Cored

FEATURES

- Composite metal cored electrode that deposits a martensitic steel with high hardness and good scaling and corrosion resistance
- · Designed to have good resistance to fire cracking, hot wear, and corrosion
- Chemistry: Fe-Mn-Cr-C
- Multiple layers may be applied with proper welding procedure
- Machinable with carbide tools
- · Good crack resistance with proper welding procedure
- · Applications include: Steel mill caster rolls, idler rolls

DIAMETERS (in (mm))

0.045 (1.2), 1/16 (1.6)

POSITIONS



SHIELDING GAS

98% Ar/2%O2, 75% Ar/ 25% CO2 Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

45-51 HRC

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO2	Flat & Horizontal	400 (10.2)	250	27	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO2	Flat & Horizontal	275 (7.0)	300	27	3/4 - 1 1/4 (19 - 32)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum *Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 4/5/2022

in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products. 600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use