

# SelectWear 420-S Plus

Hardsurfacing / Flux Shielded / Submerged Arc

PRODUCT DATA SHEET

## FEATURES

- Designed for surfacing with the submerged arc process. It has higher carbon and chromium compared with standard 420-S for added wear resistance. It can be used on the lower segments of continuous casters as well as other roll applications. Neutral flux should be used.
- Applications: Predominantly caster rolls

## DIAMETERS (in [mm])

3/32" ( ), 1/8" ( )

## POSITIONS



## FLUX

ARCFLUX BF-8.7, BF-10MW

## POLARITY

Direct Current Electrode Positive (DCEP)

## HARDNESS

49 - 54 HRC

## TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Flux	C	Cr	Fe	Mn	Si
ARCFLUX BF-10 MW	0.3	13.0	Balance	1.1	0.5

## RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Flux	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
3/32 (2.4 mm)	ARCFLUX BF 8.7	Flat & Horizontal		390	29	1 - 1 1/4 (25 - 32)
1/8 (3.2 mm)	ARCFLUX BF 8.7	Flat & Horizontal		475	29	1 - 1 1/2 (25 - 38)

\* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

## PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*\*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

## STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

Revision: 4/5/2022

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • [www.Select-Arc.com](http://www.Select-Arc.com)