

SelectWear 423-FCG

Hardsurfacing / Gas Shielded / Hardfacing

PRODUCT DATA SHEET

FEATURES

- Designed to deposit a martensitic stainless steel containing nickel and molybdenum designed for surfacing
- The deposit has improved resistance to thermal fatigue and corrosion compared to a 420 alloy
- Multiple layers may be applied with proper welding procedure
- Applications include: Caster rolls, repair to 420 type steel parts

DIAMETERS (in (mm))

1/16 (1.6), 5/64 (2.0), 3/32 (2.4)

POSITIONS



SHIELDING GAS

100% CO₂, 75% Ar / 25% CO₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

40 - 45 HRC

TYPICAL WELD DEPOSIT CHEMISTRY (WT%)

Shielding Gas	C	Cr	Fe	Mn	Mo	Ni	Si
75%Ar / 25%CO ₂	0.05	13.7	Balance	0.9	1.1	2.4	0.4

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
1/16 (1.6 mm)	75% Ar/25% CO ₂	Flat & Horizontal		270	27	3/4 - 1 (19 - 25)
5/64 (2.0 mm)	75% Ar/25% CO ₂	Flat & Horizontal	235 (6.0)	325	28	3/4 - 1 1/4 (19 - 32)
3/32 (2.4 mm)	75% Ar/25% CO ₂	Flat & Horizontal	190 (4.8)	375	29	1 - 1 1/2 (25 - 38)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

Revision: 4/5/2022

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com