

SelectWear MN-FCG

Hardsurfacing / Gas Shielded / Hardfacing

PRODUCT DATA SHEET

FEATURES

- Deposits an austenitic manganese steel which is tough, impact resistant, and work hardens in use
- Designed for severe impact and moderate abrasion
- Primarily used for the buildup and repair of manganese steel components
- Interpass temperature to be kept below 500F
- Unlimited layers can be deposited with proper welding procedure
- Applications include: Manganese steel rock crushing hammers, rolls, buckets/teeth, impactor bars, gyratory mantles, dredge components

DIAMETERS (in [mm])

0.045 (1.2), 1/16 (1.6), 5/64 (2.0), 3/32 (2.4), 7/64 (2.8), 1/8 (3.2)

POSITIONS



SHIELDING GAS

100% CO₂, 75% Ar / 25% CO₂

Flow Rate: 40 - 50 CFM

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

As welded: 15-20 HRC. After work hardening: 40-50 HRC
HRC

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
0.045 (1.2 mm)	75% Ar/25% CO ₂	Flat & Horizontal	375 (9.5)	250	27	3/4 - 1 (19 - 25)
1/16 (1.6 mm)	75% Ar/25% CO ₂	Flat & Horizontal	275 (7.0)	300	28	3/4 - 1 1/4 (19 - 32)
5/64 (2.0 mm)	75% Ar/25% CO ₂	Flat & Horizontal	235 (6.0)	325	28	3/4 - 1 1/4 (19 - 32)
3/32 (2.4 mm)	75% Ar/25% CO ₂	Flat & Horizontal	190 (4.8)	375	29	1 - 1 1/2 (25 - 38)
7/64 (2.8 mm)	75% Ar/25% CO ₂	Flat & Horizontal	165 (4.2)	400	29	1 1/4 - 1 3/4 (32 - 44)
1/8 (3.2 mm)	75% Ar/25% CO ₂	Flat & Horizontal	125 (3.2)	475	30	1 1/4 - 1 3/4 (32 - 44)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

For Welding in 100% CO₂, increase by 1 - 1.5 volts

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

*Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 10/4/2022

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 877-869-4009 • www.Select-SAI.com