SelectWear MultiPlex-MCO

Hardsurfacing / Self Shielded / Metal Cored

PRODUCT DATA SHEET

FEATURES

- Designed to produce a high concentration of uniformily distributed primary chromium carbides, along with secondary complex carbides in an austenitic matrix
- Optimized formulation results in superior weldability for a broad range of single and multiple layer applications
- The high concentration of small chromium carbides greatly improves wear resistance and toughness over conventional chromium carbide alloys
- Applications include:Multiple layer build up on coal and cement pulverizing rolls and grinding rings, ID pipe and elbow cladding, Wear plates, Sugar mill rolls, Farm implements
- · High abrasion resistance, moderate impact resistance

DIAMETERS (in (mm))

7/64 (2.8), 1/8 (3.2)

POSITIONS



SHIELDING GAS

N/A

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

2 layers: 60-65 HRC

RECOMMENDED WELDING PARAMETERS **

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
7/64 (2.8 mm)	N/A	Flat & Horizontal	220 (5.6)	470	28	1 - 1 3/4 (25 - 44)
1/8 (3.2 mm)	N/A	Flat & Horizontal	180 (4.6)	500	28	1 1/4 - 1 3/4 (32 - 44)

^{*} WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs (kgs))

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Revision: 1/17/2025

Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.

600 Enterprise Drive, P.O. Box 259, Fort Loramie, Ohio 45845-0259 • 800-341-5215 • www.Select-Arc.com

^{**}The parameters listed are recommended starting points of operation and the ranges for amperage, wfs, and voltage could be extended based on fitness for application. For products with "all-position" capability, as determined and listed in classification, the position recommendation can be determined based on operator skill and material thickness and isn't limited to the listing.

^{*}Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.