

SelectWear MultiPlex-MCO

Hardsurfacing / Self Shielded / Metal Cored

PRODUCT DATA SHEET

FEATURES

- Designed to produce a high concentration of uniformly distributed primary chromium carbides, along with secondary complex carbides in an austenitic matrix
- Optimized formulation results in superior weldability for a broad range of single and multiple layer applications
- The high concentration of small chromium carbides greatly improves wear resistance and toughness over conventional chromium carbide alloys
- Applications include: Multiple layer build up on coal and cement pulverizing rolls and grinding rings, ID pipe and elbow cladding, Wear plates, Sugar mill rolls, Farm implements
- High abrasion resistance, moderate impact resistance

DIAMETERS (in [mm])

7/64" (), 1/8" ()

POSITIONS



SHIELDING GAS

N/A

POLARITY

Direct Current Electrode Positive (DCEP)

HARDNESS

2 layers: 60-65 HRC

RECOMMENDED WELDING PARAMETERS

Diameter in (mm)	Shielding Gas	Position	WFS* in/min (m/min)	Amps	Volts	CTWD* in (mm)
7/64 (2.8 mm)	N/A	Flat & Horizontal	220 (5.6)	470	28	1 - 1 3/4 (25 - 44)
1/8 (3.2 mm)	N/A	Flat & Horizontal	180 (4.6)	500	28	1 1/4 - 1 3/4 (32 - 44)

* WFS = Wire Feed Speed, CTWD = Contact Tip To Work Distance

PACKAGING (lbs [kgs])

33 (15) Spools, 60 (27.2) Coils, 500 (226.8) Round Drum, 800 (362.9) Hex Drum, 900 (408.2) Hex Drum

**Some packaging options may not be available depending on diameter and product. Special package options may be available upon request.*

STORAGE AND HANDLING

All products should be stored in original packaging, in dry conditions and handled with care. For more information refer to our website.



Notice: Be sure to follow all your employers safety practices, policies and procedures when using this product. Refer to CSA W117.2 and ANSI Z49.1 Safety in Welding, Cutting and Allied Processes for further information and the manufactures SDS sheet. The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any particular purpose with respect to its products.